



## **Acacia Charcoal**

***Elaboration: Metallic furnaces. Processing manually through sieves  
or packing machines.***

### ***Physical-Chemistry characteristics:***



***to be able Caloric: 6100 Kca/Kg***




***burning time 3 + hours***




***Maximum humidity allowed: 3%***



***ash : 6,5%***



***Fixed carbon: 80 %***



***Volatile 19 %***



***Uniform Color; Metallic sound charcoal does not spark nor explode  
burns with flame without smoke.***



***Dimensions      graining from 20 mm up to 150mm.  
Steak – House graining***

***The Charcoal is packed in polypropylene bags of 10 kgs. properly sealed by sewn machine***

***Exported: In 40 HQ containers without palletizing with not less than 18.5 tons.***



Charcoal-Trade International    Owner: Oliver Peiseler  
Krähwinkeler Weg 23 D, 42799 Leichlingen

00492174 - 39558      charcoal-trade@online.de