



Quebracho Charcoal

Elaboration: Traditional furnaces. Processing manually through sieves or packing machines.

Physical-Chemistry characteristics:



to be able Caloric: 6800 - 7000Kca/Kg




burning time 4 - 5 hours




Maximum humidity allowed: 2%



ash : 4%



Fixed carbon: 75 %



Volatile 20 %



***Uniform Color; Metallic sound charcoal does not spark nor explode
burns with flame without smoke.***



Dimensions: graining from 50 mm up to 150mm.

Steak – House graining

***The Charcoal is packed in polypropylene bags of 15 or 20kgs.
properly sealed by machine***

Exported: In 40 HQ containers without palletizing with not less than 19,5 tons.



Charcoal-Trade International Owner: Oliver Peiseler
Krähwinkeler Weg 23 D, D - 42799 Leichlingen

00492174 - 39558 charcoal-trade@online.de